

AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions and listings of claims in the application:

1. (Currently Amended) A method for preparing managanese-based nitride the method comprising:
 - placing a mixture of Mn_2N and Cu in a quartz tube;
 - evacuating the tube;
 - sealing the tube; and
 - sintering the mixture at a temperature of from ~~about~~ 800°C to ~~about~~ 900°C to generate a manganese-based nitride having a cubic antiperovskite structure.
2. (Previously Amended) The method of claim 1, wherein Mn_2N is included in the mixture in a molar ratio of 1.45-1.55 per mole of copper.
3. (Previously Amended) The method of claim 1, further comprising:
 - heating the mixture at a rate of 40-50°C/h after sealing the tube.
4. (Previously Amended) The method of claim 1, wherein said mixture is wrapped with tantalum foil before being placed into the quartz tube.

FINNEGAN
HENDERSON
FARABOW
GARRETT &
DUNNER LLP

1300 I Street, NW
Washington, DC 20005
202.408.4000
Fax 202.408.4400
www.finnegan.com

5. (Previously Amended) A manganese-based nitride of the formula CuNMn_3 and having a temperature coefficient of resistivity of 40-50 ppm/K and a cubic antiperovskite structure.

6. (Previously submitted) The method of claim 1, wherein the manganese-based nitride has the formula CuNMn_3 .

7. (Previously submitted) The method of claim 1, wherein sintering the mixture is performed for a time of between 40 hours and 60 hours.

8. (Currently Amended) A manganese-based nitride material comprising:
copper, nitrogen, and manganese according to the formula, CuNMn_3 ;
wherein the material has a cubic antiperovskite structure; and
wherein the material has a temperature coefficient of resistivity of between about 40 ppm/K and 50 ppm/K over a temperature range of about 160 K to about 350 K.

9. (Previously submitted) The manganese-based nitride material of claim 8, wherein the cubic antiperovskite structure of the material has a space group $Pm3m$ and a lattice parameter of $a=3.90465(9) \text{ \AA}$.

FINNEGAN
HENDERSON
FARABOW
GARRETT &
DUNNER LLP

1300 I Street, NW
Washington, DC 20005
202.408.4000
Fax 202.408.4400
www.finnegan.com